# **Emulsion Protective Films**

# <u>FPP-1</u>

FPP-1 has an improved non-stick surface which allows for longer phototool life. The FPP-1 will withstand repeated exposures with less ink transfer than other protective films.

### <Structure>

#### FPP-1

Surface Treatment		
<b>PET 6</b> μ		
Adhesive layer 4 μ		
Release Liner 25 $\mu$		

Base Film	Adhesive Layer	Release Liner
6 μ	4 μ	$25\mu$

### <Properties>

	FPP-1
Total Light Transmittance (%)	91.2
Parallel Light Transmittance (%)	88.9
UV Light Transmittance (% / 365nm)	86.8
UV Light Transmittance (% / 420nm)	88.3
Haze (%)	2.5
Adhesive force for PET	2.3N / 25mm